


What is claimed is:

1. ϵ -Polylysine represented by the following formula (1),
 having a polyorganosiloxane group introduced into the
 5 molecule (a polymer hereinafter referred to as "silicone-
 modified ϵ -polylysine").




wherein B^1 , B^2 and B^3 are groups represented by general
 formula (2) below or amino groups, and at least one thereof
 10 is a group represented by formula (2), c is an integer of 0
 to 50, d is an integer of 0 to 50, and $c + d$ is an integer
 of 1 to 50.

-D-Y-Q (2)

wherein D is a group represented by:


10




a + b is an integer of 1 to 1000, and A^{11} , A^{21} and A^{31} are independently R^1 , a monovalent residue which is a compound represented by formula (1) with Q removed, or a single bond, with one thereof being a single bond.

5

2. Silicone-modified ϵ -polylysine according to claim 1, wherein D in formula (2) is one of the following groups.



3. Silicone-modified ϵ -polylysine according to claim 1,
10 wherein D in formula (2) is one of the following groups.




wherein R^{11} is C1-5 linear or branched alkylene, C2-5 alkenylene or C6-10 arylene.

15


4. Silicone-modified ϵ -polylysine according to claim 1,

wherein D in formula (2) is one of the following groups.




5. Silicone-modified ϵ -polylysine according to claim 1,
wherein D in formula (2) is one of the following groups.

5




6. A process for production of silicone-modified ϵ -
polylysine represented by formula (1), obtained by reacting
 ϵ -polylysine represented by the following formula (4) with a
10 polyorganosiloxane having a functional group which can react
with the amino groups of ϵ -polylysine.




wherein n is a integer of 2 to 50.


15



wherein B^1 , B^2 and B^3 are groups represented by general formula (2) below or amino groups, and at least one thereof is a group represented by formula (2), c is an integer of 0 to 50, d is an integer of 0 to 50, and $c + d$ is an integer of 1 to 50.




wherein D is a group represented by:



wherein R^{11} is C1-5 linear or branched alkylene, C2-5 alkenylene or C6-10 arylene), and Y is C1-1000 linear or branched alkylene, of which any mutually non-adjacent methylenes may be substituted with $-O-$, and Q is a

polyorganosiloxane group represented by the following
formula (3):



5 wherein each R^1 is independently C1-20 alkyl or C6-10 aryl,
a is an integer of 0 to 1000, b is an integer of 0 to 1000,
a + b is an integer of 1 to 1000, and A^{11} , A^{21} and A^{31} are
independently R^1 , a monovalent residue which is a compound
represented by formula (1) with Q removed, or a single bond,
10 with one thereof being a single bond.

7. A process for production of silicone-modified ϵ -
polylysine according to claim 6, wherein the
polyorganosiloxane having a functional group which can react
15 with the amino groups of ϵ -polylysine is a
polyorganosiloxane with an epoxy group.

8. A process for production of silicone-modified ϵ -
polylysine according to claim 6, wherein the
20 polyorganosiloxane having a functional group which can react
with the amino groups of ϵ -polylysine is a
polyorganosiloxane with carboxylic acid or a carboxylic acid

derivative as the functional group.


9. A process for production of silicone-modified ϵ -polylysine according to claim 6, wherein the
5 polyorganosiloxane having a functional group which can react with the amino groups of ϵ -polylysine is a polyorganosiloxane with a halogenated alkyl group.

10. A process for production of silicone-modified ϵ -polylysine according to claim 6, wherein the
10 polyorganosiloxane having a functional group which can react with the amino groups of ϵ -polylysine is a polyorganosiloxane with an unsaturated group.

15 11. An antimicrobial agent comprising an amino group-containing antimicrobial polymer having a polyorganosiloxane group introduced into the molecule (the polymer being hereinafter referred to as "silicone-modified antimicrobial polymer" and the antimicrobial agent being hereinafter
20 referred to as "silicone-modified antimicrobial agent").

12. A silicone-modified antimicrobial agent according to claim 11, wherein the silicone-modified antimicrobial polymer is a polymer obtained by reacting an amino group-
25 containing antimicrobial polymer and a polyorganosiloxane


having a functional group which can react with amino groups, represented by formula (5) below.



5 wherein R^1 is C1-20 alkyl or C6-10 aryl, a is an integer of 0 to 1000, b is an integer of 0 to 1000, $a + b$ is an integer of 1 to 1000, A^1 , A^2 and A^3 are each a group represented by formula (6) below, C1-20 alkyl or C6-10 aryl, and at least one among A^1 , A^2 and A^3 is a group represented by formula (6),

10 $-Y-Z \quad (6)$

wherein Y represents C1-1000 alkylene, of which any mutually non-adjacent methylenes may be substituted with $-O-$, and Z is one of the following groups.




wherein R^2 is C1-5 alkylene, C2-5 alkenylene or C6-10 arylene, R^3 is C1-20 alkyl, C6-10 aryl or trimethylsilyl, and X is chlorine, bromine or iodine.

5


13 A silicone-modified antimicrobial agent according to claim 12, wherein the amino group-containing antimicrobial polymer is ϵ -polylysine.

10 14 A silicone-modified antimicrobial agent according to claim 12, wherein Z in formula (6) is one of the following groups.




15 A silicone-modified antimicrobial agent according to

claim 13, wherein Z in formula (6) is one of the following groups.




16. A silicone-modified antimicrobial agent according to
5 claim 12, wherein Z in formula (6) is one of the following groups.



wherein R^2 is C1-5 alkylene, C2-5 alkenylene or C6-10
arylene.

10


17. A silicone-modified antimicrobial agent according to
claim 13, wherein Z in formula (6) is one of the following
groups.



15 wherein R^2 is C1-5 alkylene, C2-5 alkenylene or C6-10
arylene.


18 A silicone-modified antimicrobial agent according to
claim 12, wherein Z in formula (6) is one of the following

groups.



wherein R² is C1-5 alkylene, C2-5 alkenylene or C6-10
arylene, R³ is C1-20 alkyl, C6-10 aryl or trimethylsilyl,
5 and X is chlorine, bromine or iodine.

19 A silicone-modified antimicrobial agent according to
claim 13, wherein Z in formula (6) is one of the following
groups.



10


wherein R² is C1-5 alkylene, C2-5 alkenylene or C6-10 arylene, R³ is C1-20 alkyl, C6-10 aryl or trimethylsilyl, and X is chlorine, bromine or iodine.

15 20 A silicone-modified antimicrobial agent according to
claim 12, wherein Z in formula (6) is chlorine, bromine or

iodine.


21 A silicone-modified antimicrobial agent according to claim 13, wherein Z in formula (6) is chlorine, bromine or
5 iodine.

22 A silicone-modified antimicrobial agent according to claim 12, wherein Z in formula (6) is one of the following groups.



10

23 A silicone-modified antimicrobial agent according to claim 13, wherein Z in formula (6) is one of the following groups.



15 24. An antimicrobial agent according to claim 12, wherein the residual ratio of the number of amino groups of the amino group-containing antimicrobial polymer is 10-99%.

25 An antimicrobial resin composition comprising an

antimicrobial agent according to claim 11 and a resin.

26 An antimicrobial resin composition according to claim 25, wherein the resin is a synthetic resin.

5

27. An antimicrobial resin composition according to claim 26, wherein the synthetic resin is a vinyl-based polymer.

28. An antimicrobial resin composition according to claim 10 26, wherein the synthetic resin is a polyolefin-based resin.

29. An antimicrobial resin composition according to claim 26, wherein the synthetic resin is a silicone-based resin.

15 30. An antimicrobial resin composition according to claim 26, wherein the synthetic resin is an acrylic resin.

31. An antimicrobial resin composition according to claim 26, wherein the synthetic resin is an epoxy resin.